

DURA IMPEX.

505, Morya Classic, Opp. Infinity Mall, Off. Link Road, Andheri – West,
Mumbai – 400 058, India. Tel: +91 22 26744053 /26733561

Materials Specification



<u>Test</u>	<u>Conditions</u>	<u>Units</u>	<u>PP Red</u>	<u>PP Blue</u>	<u>PP Green</u>	<u>PP Black</u>
MFI	230°C /2.16Kg	g/10min	31.6	24	24.4	13.1
Ash	Lid on, 15min@700°C	%	-	-	-	3.34
Total Ash	Lid Off, total burn@700°C	%	-	-	-	2.40
Moisture	20 min/80°C	%	-	-	-	0.01
Notched Izod	ASTM D256A	J/m	-	-	-	87.4
Notched Izod	ISO Standard	kJ/M ²	-	-	-	6.8

** Data described above are Dura Impex's test data.